



## Technical Data Sheet

# DOWSIL™ 3145 RTV MIL-A-46146 Adhesive/Sealant – Gray

Gray, non-flowing adhesive, high tensile strength and elongation, enhanced thermal stability, MIL-A-46146

### Features & Benefits

- Non-flowing
- Room temperature cure
- High tensile strength and elongation
- Enhanced thermal stability
- MIL-A-46146 Group II/III, TY I
- No mixing required
- RT cure, no ovens required
- Faster in-line processing with optional heat acceleration
- Can be considered for uses with Mil Spec requirements
- Can be considered for uses needing special high temperature stability

### Composition

- One part
- Polydimethylsiloxane adhesive

### Applications

DOWSIL™ 3145 RTV MIL-A-46146 Adhesive/Sealant – Gray is suitable for:

- Sealing openings in modules and housings
- Adding mechanical stability to individual components
- Assembly of components on PWBs
- Sealing in and around wired and electrical leads
- Yoke assembly

### Application Methods

- Automated or manual needle dispense

### Typical Properties

Specification Writers: These values are not intended for use in preparing specifications.

Property	Unit	Result
Extrusion Rate	g/min	121
Flow Rate - Slump	in cm	0.1 0.2
Tack-Free Time at 25°C	minutes	78
Specific Gravity (Cured)		1.12

UNRESTRICTED – May be shared with anyone

™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

DOWSIL™ 3145 RTV MIL-A-46146 Adhesive/Sealant – Gray

© 2018 The Dow Chemical Company. All rights reserved.

## Typical Properties (Cont.)

Property	Unit	Result
NVC (Non Volatile Content)	%	96.2
Tensile Strength	psi	1035
	MPa	7.1
	kg/cm <sup>2</sup>	71
Elongation	%	670
Tensile Modulus	psi	150
	MPa	1.1
	kg/cm <sup>2</sup>	11
Tear Strength (Die B)	ppi	190
	N/cm	132
Durometer Shore A		51
Unprimed Adhesion - 180 Degree Peel Strength	ppi	106
	N/cm	72.5
Hardening Transition by DSC	°F	-43.6
	°C	-42
Shelf Life at 25°C	months	12
Mil Specification		MIL-A-46146 Group II/III, TY I

### Description

DOWSIL™ 3145 RTV one-part moisture cure adhesives are generally cured at room temperature and in an environment of 30 to 80 percent relative humidity eliminating the need for curing ovens and the associated costs of energy and capital. Greater than 90 percent of full physical properties should be attained within 24 to 72 hours and varies according to product. Faster manufacturing through-put can be achieved since the adhesive and component can be handled in much shorter times of about 10 to 120 minutes, depending on the adhesive selected and the amount applied.

These adhesives are not typically used in highly confined spaces or where a deep section cure is required as they generally cure from the exposed surface inward at a rate of 0.25 inch per seven days. Cure progresses from the outer exposed surface and is dependent on the moisture in the air. Working time is generally a few minutes to an hour for these products until a surface skin begins to form. Mild heat below 60°C (140°F) may be used to increase through-put by accelerating the cure.

DOWSIL™ silicone adhesives retain their original physical and electrical properties over a broad range of operating conditions which enhance the reliability of and service life of devices. The stable chemistry and versatile processing options of these adhesives offer benefits for a variety of electronics needs from increasing component safety and reliability, reducing total cost or increasing the performance envelope of devices or modules. Underwriters Laboratory (UL) 94 recognition is based on minimum thickness requirements. Please consult the UL Online Certifications Directory for the most accurate certification information.

UNRESTRICTED – May be shared with anyone

®™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

DOWSIL™ 3145 RTV MIL-A-46146 Adhesive/Sealant – Gray

© 2018 The Dow Chemical Company. All rights reserved.

Preparing Surfaces	All surfaces should be thoroughly cleaned and/or degreased with DOWSIL™ OS Fluids, naphtha, mineral spirits, methyl ethyl ketone (MEK) or other suitable solvent. Solvents such as acetone or isopropyl alcohol (IPA) do not tend to remove oils well, and any oils remaining on the surface may interfere with adhesion. Light surface abrasion is recommended whenever possible, because it promotes good cleaning and increases the surface area for bonding. A final surface wipe with acetone or IPA is also useful. Some cleaning techniques may provide better results than others; users should determine the best techniques for their particular applications.
Substrate Testing	Due to the wide variety of substrate types and differences in substrate surface conditions, general statements on adhesion and bond strength are impossible. To ensure maximum bond strength on a particular substrate, 100 percent cohesive failure of the adhesive in a lap shear or similar adhesive strength test is desired. This ensures compatibility of the adhesive with the substrate being considered. Also, this test can be used to determine minimum cure time or can detect the presence of surface contaminants such as mold release agents, oils, greases and oxide films.
Adhesion	DOWSIL™ silicone adhesives are specially formulated to provide unprimed adhesion to many reactive metals, ceramics and glass, as well as to selected laminates, resins and plastics. However, good adhesion cannot be expected on non-reactive metal substrates or non-reactive plastic surfaces such as Teflon®, polyethylene or polypropylene. Special surface treatments such as chemical etching or plasma treatment can sometimes provide a reactive surface and promote adhesion to these types of substrates. DOWSIL™ Primers can be used to increase the chemical activity on difficult substrates. Poor adhesion may be experienced on plastic or rubber substrates that are highly plasticized, because the mobile plasticizers act as release agents. Small-scale laboratory evaluation of all substrates is recommended before production trials are made.
Useful Temperature Ranges	For most uses, silicone elastomers should be operational over a temperature range of -45 to 200°C (-49 to 392°F) for long periods of time. However, at both the low- and high temperature ends of the spectrum, behavior of the materials and performance in particular applications can become more complex and require additional considerations. For low-temperature performance, thermal cycling to conditions such as -55°C (-67°F) may be possible, but performance should be verified for your parts or assemblies. Factors that may influence performance are configuration and stress sensitivity of components, cooling rates and hold times, and prior temperature history. At the high-temperature end, the durability of the cured silicone elastomer is time and temperature dependent. As expected, the higher the temperature, the shorter the time the material will remain useable.
Solvent Exposure	When liquid or vapor solvent or fuel exposure can occur in an application, the silicone adhesive discussed in this brochure is intended only to survive splash or intermittent exposures. It is not suited for continuous solvent or fuel exposure. Testing should be done to confirm performance of the adhesives under these conditions.

Handling Precautions	PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE SAFETY DATA SHEET IS AVAILABLE ON THE DOW WEBSITE AT CONSUMER.DOW.COM, OR FROM YOUR DOW SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CUSTOMER SERVICE.
Usable Life and Storage	For best results, DOWSIL™ RTV adhesives should be stored at or below the storage temperature listed on the product label. Special precautions must be taken to prevent moisture from contacting these materials. Containers should be kept tightly closed with head or air space minimized. Partially filled containers should be purged with dry air or other gases, such as nitrogen. Shelf life is indicated by the "Use Before" date found on the product label.
Packaging Information	DOWSIL™ RTV Adhesives are typically packaged in 100 ml syringes and 330 ml cartridges, 1 kg tubs and pails (18–25 kg). In general, DOWSIL™ RTV adhesives/sealants are supplied in nominal 0.45-, 3.6-, 18- and 200-kg (1-, 8-, 40- and 440-lb) containers, net weight. Not all products may be available in all packages and some additional packages, such as a bladder packs or tubes, may be available for certain package sizes.
Limitations	This product is neither tested nor represented as suitable for medical or pharmaceutical uses.
Health And Environmental Information	To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.  For further information, please see our website, <a href="http://consumer.dow.com">consumer.dow.com</a> or consult your local Dow representative.
How Can We Help You Today?	Tell us about your performance, design and manufacturing challenges. Let us put our silicon-based materials expertise, application knowledge and processing experience to work for you.  <b>For more information</b> about our materials and capabilities, visit <a href="http://consumer.dow.com">consumer.dow.com</a> .  To discuss how we could work together to meet your specific needs, go to <a href="http://consumer.dow.com">consumer.dow.com</a> for a contact close to your location. Dow has customer service teams, science and technology centers, application support teams, sales offices and manufacturing sites around the globe.

consumer.dow.com

**LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY**

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.**

**DOW DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.**

