

Aeriol 
ThixO #2 Aviation Grease

Aeriol Thixo#2 Aviation Grease is specifically engineered to provide outstanding results in the most extreme conditions. The incredible flexibility in performance allows the grease to be used in a wide range of aviation applications

Aeriol ThixO#2 Aviation Grease uses an advanced thickening agent and superior additive technology which exhibits a high resistance to water washout and has excellent thermal and oxidation stability which can result in longer component life and increased productive. Aeriol ThixO#2 Aviation Grease demonstrated outstanding sheer stability and exhibits a broad temperature range (-35°C to >250°C).

Approved for use on helicopter and aviation equipment in areas as specified by the OEM. Aeriol ThixO#2 Aviation Grease has received many regional approvals for specific models by the Civil Aviation Authority in New Zealand, Transport Canada, and other countries worldwide.

Aeriol ThixO#2 Aviation Grease is approved and recommended for use in wide range of Bell Helicopter models for specific application primarily as a CPC to prevent corrosion and seizing of critical components in simple nuts, bolts as well as drives, hub sets and splines.

Meets or Exceeds the following Bell Consumable Material Ref C-561.

Aeriol ThixO#2 Aviation Grease: For use in Aviation (fixed and rotary wing?) greasing applications as specified by the OEM. Aeriol ThixO#2 Aviation Grease should not be considered an alternate for other greases in all applications. Be sure to carefully read and apply all instructions found in the maintenance manuals and technically service bulletins published by the OEM

PART #	3810-1 (425g Tube x 10)	3811-0 (17kg Pail)	3813-0 (180kg Drum)
	3810-0 (425g Tube x 60)	3812-0 (55kg Keg)	

<u>TYPICAL PROPERTIES</u>	<u>ASTM METHOD</u>	<u>Aeriol ThixO#2 Aviation Grease</u>
NLGI Consistency Grade		2
Appearance		Brown, Smooth, Buttery
Worked Penetration (60 Strokes – mm/10)	D 217	280
Dropping Point (°C)	D 2265	>300 (572°F)
Oil Separation (% W Loss)	D 1742	0.27

<u>Base Oil</u>		
Viscosity @ 40°C (cSt)	D 445	130
Viscosity @ 100°C (cSt)	D 445	13.4
Viscosity Index	D 2270	95
Specific Gravity	D 1298	1.05
Density 20°C (g/ml)	D 1298	1.05
Pour Point (°C)	D 97	-15°C (5°F)

Aeriol
ThixO #2 Aviation Grease
LUBRICANTS | Reach New Heights

Performance Testing		
Timken OK Load (kg)	D 2509	> 31 (70 lbs)
4 Ball EP - Load Wear Index	D 2596	75
4 Ball EP - Weld Point (kgf)	D 2596	500
4 Ball EP - Weld Point (kgf)	D 2596	500
Water Washout (% loss @ 80°C (175°F))	D 1264	0.10%
Wheel Bearing Leakage (g loss)	D 4290	3.94
Low Temperature Torque (Nm @ -40°C)	D 4693	12
Corrosion Prevention	D 1743	PASS